

# Carbopol<sup>®</sup> 940 Polymer

## General

**Appearance:** White powder

**Odor:** Slightly acetic

**INCI Name:** Carbomer

	% SOLUTION	MINIMUM	MAXIMUM	TEST FREQUENCY	LUBRIZOL TEST PROCEDURE NUMBER
<b>Brookfield RVF or RVT Viscosity, (mPa-s):</b> (20 rpm at 25°C, neutralized solutions)	0.2 0.5 1.0	19,000 40,000 45,000	35,000 60,000 80,000	Once/20 Lots Each Lot Once/20 Lots	<a href="#">TP-430-I</a>
<b>Moisture Content, %:</b>	--	--	2.0	Once/10 Lots	<a href="#">TP-SA-004</a>
<b>Heavy Metals, ppm:</b> (Pb, As, Hg, Sb)	--	--	10	Once/200 Lots	<a href="#">TP-SA-012</a>
<b>Clarity, % Transmission:</b> (neutralized solution, 420 nM light)	0.5	85	--	Each Lot	<a href="#">TP-485-D</a>
<b>Residual Benzene, %*:</b>	--	--	0.5	Each Lot	<a href="#">TP-SA-006</a>

Previous Edition: July 7, 1997

\*Lubrizon Advanced Materials, Inc. supplies Carbopol 934, 940 and 941 polymers to meet the Residual Benzene level of 0.1% maximum required by Canada, the European Union and Korea.

**Lubrizon Advanced Materials, Inc. / 9911 Brecksville Road, Cleveland, Ohio 44141-3247 / TEL: 800.379.5389 or 216.447.5000**

The information contained herein is believed to be reliable, but no representations, guarantees or warranties of any kind are made as to its accuracy, suitability for a particular application or the results to be obtained herefrom. Lubrizon Advanced Materials, Inc. ("Lubrizon") cannot guarantee how any products associated with this information will perform in combination with other substances or in your process as the "user". Often, the information is based on laboratory work with small-scale equipment. Due to variations in

methods, conditions and equipment used commercially in processing materials, the information does not necessarily indicate end product performance or reproducibility. As such, no warranties or guarantees are made as to the suitability of the information or products referenced hereunder for any applications disclosed to Lubrizon. Full scale testing and end product performance are the responsibility of the user. Further, any formulations presented should be used only as a suggested starting point. Lubrizon shall not be liable and

the user assumes all risk and responsibility for, any use or handling of any material beyond Lubrizon's direct control. THE SELLER MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, THE IMPLIED WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. Nothing contained herein is to be considered as a permission, recommendation, or as an inducement to practice any patented invention without permission of the patent owner.

For further information, please visit: [www.lubrizon.com/personalcare](http://www.lubrizon.com/personalcare)